A Study of the Degree of Fluorination in Regioregular Poly(3-hexylthiophene)

Citation

Blaskovits, J. Terence, Thomas Bura, Serge Beaupré, Steven A. Lopez, Carl Roy, Julio de Goes Soares, Adam Oh, et al. 2016. "A Study of the Degree of Fluorination in Regioregular Poly(3-Hexylthiophene)." *Macromolecules* 50 (1) (December 27): 162–174. doi:10.1021/acs.macromol.6b02365.

Published Version

doi:10.1021/acs.macromol.6b02365

Permanent link

<http://nrs.harvard.edu/urn-3:HUL.InstRepos:35164984>

Terms of Use

This article was downloaded from Harvard University's DASH repository, and is made available under the terms and conditions applicable to Open Access Policy Articles, as set forth at <http://nrs.harvard.edu/urn-3:HUL.InstRepos:dash.current.terms-of-use#OAP>

Share Your Story

The Harvard community has made this article openly available.
Please share how this access benefits you. [Submit a story](#).

[Accessibility](#)

A Study of the Degree of Fluorination in Regioregular Poly(3-hexylthiophene)

J. Terence Blaskovits^{1#}, Thomas Bura^{1#}, Serge Beaupré¹, Steven A. Lopez², Carl Roy¹, Julio de Goes Soares², Adam Oh², Jesse Quinn³, Yuning Li³, Alán Aspuru-Guzik², Mario Leclerc^{1*}

J.T.B. and T.B. contributed equally

[*] Prof. Mario Leclerc

1) Canada Research Chair on Electroactive and Photoactive Polymers, Department of Chemistry, Université Laval, Quebec City, Quebec, Canada

2) Department of Chemistry and Chemical Biology, Harvard University, Cambridge, Massachusetts, U.S.A.

3) Department of Chemical Engineering, University of Waterloo, Waterloo, Ontario, Canada

E-mail : Mario.Leclerc@chm.ulaval.ca

For Table of Contents Use Only:

Abstract

We systematically varied the degree of fluorination along the backbone of a series of highly regioregular 3-hexylthiophene-based polymers, **P3HT-50F**, **P3HT-33F** and **P3HT-25F**, in which 50%, 33% and 25% of the thiophene units within the polymer chain contain fluorine atoms in the available 4-position. These materials were homopolymerized using the Kumada catalyst transfer polycondensation method from a set of mono-fluorinated bi-, ter- and quarterthiophenes, to ensure high polymer regioregularity and evenly-spaced fluorine atoms along the conjugated thiophene backbone. The monomers were obtained from a synthetic route consisting of iterative Migita-Stille couplings of fluorinated and non-fluorinated 3-hexylthiophenes. The effect of the fluorine atoms on both polymer structure and properties is presented, with supporting quantum mechanical calculations that rationalize the intrinsic conformation preferences of the three P3HT derivatives. **P3HT-50F** ($\bar{M}_n = 34$ kg/mol, 98.5% rr), **P3HT-33F** ($\bar{M}_n = 46$ kg/mol, 98% rr) and **P3HT-25F** ($\bar{M}_n = 53$ kg/mol, 95% rr) displayed HOMO levels of -5.34, -5.26 and -5.24 eV, bandgaps of 1.98, 1.98 and 1.97 eV, and average field-effect transistor hole mobilities of 4.5×10^{-3} , 2.7×10^{-2} , and 1.2×10^{-2} cm² V⁻¹ s⁻¹, respectively.

Introduction

The impact of incorporating fluorine atoms into conjugated polymers has been the subject of much investigation. The incorporation of fluorine onto conjugated systems favors π - π stacking,^{1, 2} and often results in a decrease of both the HOMO and LUMO frontier molecular orbital energies.^{3, 4} The bandgap is thus constant, leading to a maintained absorption range of the material, while increasing the open-circuit voltage (V_{OC}) in bulk heterojunction solar cells.⁵ The electronegativity of fluorine atoms can result in additional non-covalent interactions with adjacent repeating units which possess sulfur or hydrogen atoms in close spatial proximity to the fluorine moiety. These interactions promote coplanarity within a polymer chain, and strengthen inter- and intra-chain interactions.^{6, 7} However, the impact of fluorination on polymer morphology remains unpredictable, and both reduced solubility during polymerization and aggregation during device fabrication should be considered carefully when working with fluorinated homo- and copolymers.⁸ Fluorination at the 3-position of some thiophene-based units of conjugated polymers increases both the difficulty and cost of monomer synthesis, potentially limiting large-scale applications of these materials.

A number of studies have focused specifically on the preparation of fluorinated polythiophenes. These are summarized in **Figure 1**. Following initial reports of the electropolymerization of 3-fluorothiophene⁹ and the synthesis of a perfluorinated oligothiophene¹⁰ in the early 2000s, a patent describing different synthetic routes to obtain poly(3-alkylthiophene) derivatives with fluorinated backbones was presented.¹¹ Drawing on these synthetic procedures, Roncali and colleagues have since described the electropolymerization of an alkylated mono-fluorinated terthiophene.¹² Swager *et al.* also post-functionalized a brominated poly(3-hexylthiophene) at the 4-position using various electrophilic reagents.¹³ Using this method, the authors were able to

incorporate fluorine atoms into 67% of the thiophene units using *N*-fluorobenzenesulfonimide (NFSI).

Two recently reported methods describe the synthesis of fluorinated thiophene monomers which were then polymerized using polycondensation techniques. First, the Kumada catalyst transfer polycondensation (KCTP) of 2,5-dibromo-3-fluoro-4-hexylthiophene resulted in a relatively regioregular (93% regioregularity) fluorinated poly(3-hexylthiophene) (P3HT) by Heeney *et al.*¹⁴ However, the resulting polymer displayed very low solubility, and further characterization could not be undertaken. The authors then prepared analogue polymers with octyl and ethylhexyl side chains to improve solubility and better compare the effect of fluorination. All three fluorinated poly(3-alkyl)thiophenes displayed improved charge carrier mobilities despite a lower degree of crystallinity (as compared to P3HT), which may result from increased coplanarity, as indicated by conformational analysis using density functional theory (DFT). Second, Coughlin and co-workers increased the solubility of fluorinated P3HT via a direct (hetero)arylation (DHAP) protocol.¹⁵ This was performed by varying the initial ratio of two monomers: 2-bromo-3-hexylthiophene and 2-bromo-4-fluoro-3-hexylthiophene. However, with an increase in fluorinated thiophene content from 25 to 100%, regioregularity dropped systematically from 89% to 78%. Hole mobility of approximately $2\text{--}3 \times 10^{-5} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$ (as determined by the space charge limited current method) and power conversion efficiency (PCE) of OPV devices also decreased with increased fluorination. The phenomenon of reduced PCE with reduced regioregularity has been previously observed in non-fluorinated P3HT.¹⁶ In the DHAP reaction, the presence of an electron-withdrawing group adjacent to the desired C-H bond increases reactivity,¹⁷ which may have an adverse effect on the random nature of such a fluorinated copolymer. In addition to this, the authors used DHAP conditions suitable for copolymers but

necessarily optimal for the preparation of poly(3-alkyl)thiophenes.¹⁸ These factors rendered an assessment of the impact of the random incorporation of fluorinated thiophene units into a P3HT chain difficult.

Figure 1. A summary of the synthesis of various fluorinated oligo- and polythiophenes from 1994 to the present: a) the electropolymerization of 3-fluorothiophene;⁹ b) the step-wise

1
2
3 synthesis of tetradecafluorosexithiophene;¹⁰ c) the electropolymerization of an alkylated mono-
4 fluorinated terthiophene;¹² d) the post-functionalization of brominated P3HT with the
5 electrophilic fluorine source *N*-fluorobenzenesulfonimide (NFSI);¹³ e) the KCTP of 2,5-dibromo-
6 3-fluoro-4-alkylthiophenes;¹⁴ f) the random DHAP copolymerization of 2-bromo-4-fluoro-3-
7 hexylthiophene with 2-bromo-3-hexylthiophene;¹⁵ g) this report.

8
9
10
11
12
13
14
15
16
17
18
19 For this reason, we synthesized a series of highly regioregular fluorinated P3HT-based
20 homopolymers via iterative thiophene couplings. We wished to assess the influence of
21 fluorination on the optical and electronic properties of P3HT, especially with regards to the
22 degree of fluorination required to modulate the HOMO and bandgap of P3HT. This experiment
23 also served to determine if the increasing, precisely ordered presence of fluorine atoms along the
24 polymer backbone leads to a change in charge-carrier mobility through electronic or steric
25 influences. Kumada catalyst transfer polycondensation (KCTP) was used to allow more direct
26 comparison with previously reported fully-fluorinated P3HT derivatives, which have been also
27 prepared using this method.¹⁴

28 29 30 31 32 33 34 35 36 37 38 39 40 41 42 43 44 45 **Results and Discussion**

46 47 48 **1. Monomer Synthesis**

49
50
51 The starting fluorinated unit 2-bromo-4-fluoro-3-hexylthiophene (**2Br4F3HT**) was synthesized
52 according to previously reported methods,¹⁰⁻¹² albeit with a slight modification to the protocol of
53 the fluorination step (see **Supporting Information**). The bromine-fluorine halogen exchange
54
55
56
57
58
59
60

was undertaken with both the organolithium reaction mixture and the solution of freshly recrystallized *N*-fluorobenzenesulfonimide (NFSI) at $-100\text{ }^{\circ}\text{C}$. This differs from previously recorded protocols, in which the reaction mixture was cooled to $-78\text{ }^{\circ}\text{C}$ and the solution of NFSI was maintained at room temperature. The NFSI used was also freshly recrystallized in diethyl ether, according to a previously reported protocol.¹⁰ In this way, less dehalogenation was observed at the 3-position of the thiophene, and the isolated yield for this step was consequently improved from approximately 50 to 65%.

A series of iterative stannylation reactions and Migita-Stille couplings was then undertaken in order to obtain compounds **4**, **6** and **8** (as shown in **Figure 2**), in a similar fashion to a previous report.¹⁹ In each case, the 2-position of the thiophene was protected with a trimethylsilyl moiety in order to prevent stannylation at this position. An initial synthetic approach using *n*-butyllithium with tetramethylethylenediamine (TMEDA) was attempted in order to selectively insert the organotin moiety in the 5-position. As noted by Smith and Barratt,²⁰ the use of amine ligands or even sterically hindered lithium amide reagents such as LiTMP (lithium 2,2,6,6-tetramethylpiperidide) do not entirely eliminate the possibility of a mixture of regioisomers following electrophilic substitution. Even with high ratios of 5-substituted to 2-substituted thiophene derivatives, the presence of irregularly stannylated thiophenes result in some undesired coupling products, rendering purification procedures more difficult.

Figure 2. Iterative synthesis of stannylthiophene derivatives **4**, **6** and **8**. Reaction conditions: i) NBS in 1:1 CHCl_3 :AcOH; ii) $n\text{-BuLi}$ in THF, -78°C , then Me_3SiCl ; iii) $n\text{-BuLi}$ in THF, -78°C , then Me_3SnCl ; iv) Pd_2dba_3 3 mol%, $\text{P}(o\text{-tol})_3$ 12 mol%, toluene, reflux.

Following the preparation of the stannylated mono-, bi- and terthiophenes, each of these was coupled to **2Br4F3HT** via Migita-Stille coupling, as presented in **Figure 3**. The desired products **9**, **11** and **13** were obtained in 88%, 84% and 95% yield, respectively, and in each case the principal side-product was isolated and identified by ^1H NMR analysis as being the result of stannylthiophene homocoupling. Once the fluorinated thiophene unit was inserted onto the thiophene chain, the monomers were readily purified using reverse-phase (C-18) flash column chromatography, which turned out to be quite advantageous, as some impurities could not be

separated from the desired product using silica as the stationary phase. This ensured the purity of the monomers and, by extension, the purity of the resulting polymers. Interestingly, the final step to obtain the di-brominated monomers **10**, **12** and **14** required three different bromination reaction conditions (see **Figure 3** for details). The bromination of **9** was performed as previously reported in numerous studies, by using N-bromosuccinimide (NBS) in a 1:1 mixture of chloroform and acetic acid, affording **10** in a 93% yield. However, these conditions led to unexpected products when applied to **11** and **13**. Following optimization of the bromination reaction, we found that the bromination of **11** with NBS afforded the desired product in acid-free chloroform. Acid-free chloroform was obtained by filtering the solvent through aluminum oxide (basic). In this way, **12** was obtained in 52% yield. NBS was found to be an ineffective brominating agent in the preparation of **14**, and 1,3-dibromo-5,5-dimethylhydantoin was employed to afford the desired product, albeit in an isolated yield of 51%. All synthetic protocols are detailed in the **Supporting Information**.

Figure 3. Synthesis of monomers from **2Br4F3HT** coupled with stannyl thiophenes **4**, **6** and **8**; polymerization of **10**, **12** and **14** to afford **P3HT-50F**, **P3HT-33F** and **P3HT-25F**, respectively.

Reaction conditions: iv) Pd₂dba₃ 3 mol%, P(*o*-tol)₃ 12 mol%, toluene, reflux; v) NBS, 1:1 CHCl₃:AcOH; vi) NBS, CHCl₃; vii) 1,3-dibromo-5,5-dimethylhydantoin, CHCl₃; viii) 0.97 mol% *i*-PrMgCl·LiCl, THF, 0 °C, then Ni(dppp)Cl₂ 1.5 mol%, 80 °C.

2. Polymer Synthesis and Structural Characterization

Polymerization of **10**, **12** and **14**, which afforded respectively **P3HT-50F**, **P3HT-33F** and **P3HT-25F**, was performed using similar conditions to those reported previously for P3HT and fluorinated P3HT.^{14, 21-23} These consisted of selectively forming the Grignard on the fluorinated thiophene using the Turbo Grignard reagent (*i*-PrMgCl·LiCl) in slightly sub-stoichiometric quantities (0.97 equivalent) at 0 °C in THF, followed by the addition of the precatalyst [1,3-bis(diphenylphosphino)propane]dichloronickel(II) (Ni(dppp)Cl₂) to the reaction mixture and heating to 80 °C. Results for the three polymers are summarized in **Table 1**, along with those of P3HT prepared by both KCTP and DHAP.²⁴

Table 1. Molecular weight, molar-mass dispersity, degree of polymerization, yield and regioregularity of **P3HT-50F**, **P3HT-33F** and **P3HT-25F**

Polymer	$\overline{M}_n$ (kg/mol) ^a	$\overline{D}_M$ ^a	DP ^b	Yield (%) ^c	RR (%) ^d
P3HT-50F	34	1.5	97	72	98.5
P3HT-33F	46	1.3	88	78	98
P3HT-25F	53	1.5	78	59	95
P3HT (KCTP) ^e	88	1.5	530	-	98
P3HT (DHAP) ^e	33	1.8	199	96	> 99

^a Number average molar mass ($\bar{M}_n$) and molar-mass dispersity ($\mathcal{D}_M$) were obtained from size exclusion chromatography (SEC) measurements. ^b Degree of polymerization (DP) was calculated from the number average molar mass using the molar weight of the repeating unit. ^c Yield was obtained following Soxhlet extraction and polymer washing. ^d Regioregularity was determined from integration of the resonances in ^{19}F NMR spectra. ^e Previously-reported samples of P3HT.²⁴

Crude polymers were precipitated in methanol and purified using Soxhlet extraction (acetone, hexane and *ortho*-dichlorobenzene [*o*-DCB]), affording **P3HT-50F**, **P3HT-33F** and **P3HT-25F** with degrees of polymerization (DP) of 97, 88 and 78, and isolated yields of 72, 78 and 59%, respectively. Despite not being extracted with chloroform or chlorobenzene, molar-mass dispersity values remained relatively and comparatively narrow for each polymer. Some insoluble material remained in the Soxhlet cartridge following the extraction of **P3HT-50F** with *o*-DCB. The polymer washing step was used in order to reduce metallic impurities, following a reported procedure for polymers prepared by the KCTP method.²⁵ **P3HT-50F** was found to be soluble in chlorinated solvents (*o*-DCB and 1,2,4-trichlorobenzene) above 100 °C, as was **P3HT-33F** around 80 °C. **P3HT-25F** was found to be soluble in these solvents at room temperature.

MALDI-ToF analysis was undertaken in order to identify end-chains (full spectra are available in the **Supporting Information**). In every case, the signature peaks separated by the molecular weight of the repeating unit was well-defined. For all three polymers, the main peak could be attributed to Br/Br end-chains and the secondary peak to the expected H/Br end-chains. Interestingly, the loss of a C_5H_{11} chain radical, which has been previously observed in P3HT²⁶

and random fluorinated P3HT¹⁵ was not identified in any of the spectra. Nor was there any evidence of *iso*-propyl endgroups, potentially originating from brominated end groups reacting with unreacted *iso*-propylmagnesium chloride. Only in **P3HT-25F** were weak signals associated with H/H end-chains found, possibly arising from magnesium-halogen exchange when the reaction mixture temporarily gellified at 80 °C (an increase in temperature to 120 °C was necessary to resolubilize the mixture).²⁷ In KCTP, H/Br is the expected endcap pair, due to the quenching of the active Grignard chain ends with methanol. In this case, we hypothesized that the prevalence of Br/Br endcapping may arise from reductive homocoupling of two Grignard chain ends (leading to the regeneration of the initial catalytic species Ni(dppp)Cl₂), or from chain termination, in which the catalytic species simply decoordinates from the polymer chain before being inserted into a new C-Br bond. This phenomenon becomes more likely as the reaction time increases.²⁸ As described above, magnesium-halogen exchange could also be a cause of the observed end-chains, but as there is very little (**P3HT-25F**) or no evidence (**P3HT-50F** and **P3HT-33F**) of the accompanying H/H originating from the quenching of the bis-Grignard polymer chain, this is unlikely. Due to the fact the molar masses observed in the MALDI-ToF spectra are considerably lower than those obtained from SEC and NMR measurements (see below), it can be presumed that only the shorter chains within the polymer sample are readily ionised when this method of characterization is used. This may lead to the disproportionately large fraction of Br/Br end capped chains observed, as these were terminated early on in the polymerization reaction. It is therefore not possible to ascertain the nature of the end groups of longer polymer chains.

Polymer regioregularity and end-chains were studied by ¹H and ¹⁹F NMR analysis in tetrachloroethane (TCE) at 110 °C, due to the limited solubility of **P3HT-50F** and **P3HT-33F** at

1
2
3 lower temperatures. The full ^1H NMR spectra as well as details of the aromatic and methylene
4 regions are shown in **Figure 4**. The signal at 2.83 ppm corresponds to the methylene of the
5 fluorinated thiophene unit, and the signal at 2.91 ppm to that of the non-fluorinated thiophene,
6 although peak multiplicity was lost due to the heating necessary to fully solubilize **P3HT-50F**
7 and **P3HT-33F**. The integration of these signals against one another serves as a tool to validate
8 the polymer structure: the resonance at both 2.83 and 2.91 ppm have the same integration value
9 in **P3HT-50F**, the resonance at 2.91 ppm is twice as intense as the resonance at 2.83 ppm **P3HT-**
10 **33F**, and three time as intense in **P3HT-25F**. This effect can be readily correlated with the
11 equivalent signals of the corresponding monomers: the well-defined triplet at *ca.* 2.57 ppm
12 corresponds to the methylene of fluorinated thiophene, and the multiplet centered on *ca.* 2.7 ppm
13 to those of all the other, non-fluorinated thiophenes. Coughlin and colleagues also observed this
14 difference in methylene signals in their study of random fluorinated P3HT copolymers.¹⁵

15
16
17 In P3HT, the chemical shift of the central aromatic proton in the HT-HT triad is 6.98 ppm. In
18 **P3HT-50F**, the principal aromatic resonance ($\text{H}_{(\text{A})}$) is found at 7.14 ppm, indicating that the 50%
19 fluorinated equivalent of P3HT in the spectral conditions used (110 °C) is downshifted by
20 approximately 0.16 ppm vis-à-vis P3HT. The combination of the electronic effect of the fluorine
21 atoms along the polymer backbone and the use of a different solvent (TCE) at a high temperature
22 modifies the absolute chemical shift of the protons, but should not change the relative shift
23 between protons. For this reason, it is possible to associate the secondary resonance visible in the
24 **P3HT-50F** spectrum at 6.96 ppm to a resonance which might appear at *ca.* 6.80 ppm in P3HT.
25 This corresponds most closely to the proton on a HT-HT brominated terminal thiophene ($\text{H}_{(\text{B})}$,
26 which is situated at 6.82 ppm in non-fluorinated P3HT), confirming the results of MALDI-ToF
27 analysis. It appears in 3% of the intensity of the principal HT-HT signal, meaning that if, as the

MALDI-ToF results indicate, the vast majority of end-chains are Br/Br, this corresponds to a degree of polymerization (DP) of 67. The fact that the DP as calculated using NMR spectra is greatly inferior to the DP as determined by SEC measurements (97) is widely documented in the characterization of conjugated polymers, including poly(thiophene)s.²⁹ This is due to the discrepancy of the hydrodynamic radius of such polymers as compared to the radii of the poly(styrene) standards used for the calibration of SEC methods.

Figure 4. Full ¹H NMR spectra (above) and detail of the aromatic and methylene regions for **P3HT-50F** (green), **P3HT-33F** (blue) and **P3HT-25F** (red) in TCE at 110 °C. The resonances at *ca.* 7.12 ppm correspond to the protons on the non-fluorinated thiophenes (H_(A)). The resonances at *ca.* 2.83 ppm correspond to the first CH₂ (methylene) of the hexyl chains of the fluorinated thiophene units (H_(C)), and those at *ca.* 2.91 ppm to the methylene on non-fluorinated thiophenes (H_(D)). H_(B) and H_(E) correspond to the aromatic and methylene protons on the end-chain units, respectively. Integration of **P3HT-50F** alone has been shown for clarity in the lower image.

1
2
3 In addition to this, HT-HH defects in P3HT appear as a signal with a shift of 7.02 ppm. This
4
5 would correspond to a resonance at 7.18 in **P3HT-50F**. There is no evidence of a resonance with
6
7 this chemical shift, consistent with the fact that head-to-head homocoupling defects do not occur
8
9 in P3HT prepared by the KCTP method.³⁰ There is no other signal visible in the aromatic region
10
11 of the ¹H NMR spectra, confirming both the polymer regioregularity and that initial TT coupling
12
13 is the only observable defect within each polymer chain.
14
15

16
17
18 In the methylene region, a single secondary resonance appears at 2.69 ppm, upshifted by 0.20
19
20 ppm from the abovementioned principal methylene resonance of the non-fluorinated thiophene
21
22 ($H_{(D)}$, 2.89 ppm). The main explanation for this is an HT dyad end group. This is supported by
23
24 the ¹H NMR spectrum of a sample of regioregular P3HT in the same analysis conditions used for
25
26 **P3HT-50F**: although all resonance resolution is lost in these conditions, the secondary
27
28 methylene resonance corresponding to the end-chains is also found at *ca.* 2.69 ppm, upshifted
29
30 from the principal resonance by 0.21 ppm (see **Supporting Information** for the P3HT
31
32 spectrum). As the principal methylene resonances ($H_{(C)}$ and $H_{(D)}$) occur in a 4:1 ratio to the
33
34 principal aromatic resonance of **P3HT-50F** ($H_{(A)}$), so should the brominated chain-end
35
36 methylene resonance appear in a 4:1 ratio to the aromatic proton on the brominated thiophene
37
38 end group. This turns out to be the case, in that the secondary resonance at 2.69 ppm corresponds
39
40 to 4% of the intensity of the two principal methylene resonances. This same reasoning was
41
42 applied to the spectra of **P3HT-33F** and **P3HT-25F**, with similar results. The secondary
43
44 resonances in the aromatic and methylene regions integrated for 3% of the principal resonances
45
46 in both **P3HT-33F** and **P3HT-25F**.
47
48
49
50
51
52

53
54 In P3HT, the TT-HT triad produced by the initiation of KCTP chain growth can be observed in
55
56 the aromatic region of ¹H NMR spectra. However, due to the presence of the fluorine atoms on
57
58
59
60

the thiophene backbone in fluorinated P3HT derivatives, this is not possible. We therefore turned to interpreting the ^{19}F NMR spectra of the three polymers for insight into the TT defect. Analyses reveal an upfield shift of the principal resonance ($F_{(A)}$) going from $\delta = -120.97$ ppm in **P3HT-50F** to $\delta = -122.43$ ppm in **P3HT-33F**, and another slight shift to $\delta = -122.50$ ppm for **P3HT-25F**. In all of these spectra, a secondary signal upfield from the principal resonance is visible, and as the rate of fluorination decreases, this resonance draws nearer to the principal resonance. In **P3HT-50F**, this resonance has 3% of the intensity of the principal resonance, and in **P3HT-33F** 4%. In **P3HT-25F** the primary and secondary signals are differentiated from one another with difficulty, but the secondary resonance shows an intensity of approximately 10% relative to the principal resonance (see **Supporting Information** for full ^1H and ^{19}F NMR spectra).

Due to the symmetrical nature of the inherent TT defect, the presence of fluorine atoms in each of the repeating units amplifies the defect twofold. If there is only one TT defect within the polymer chain, the 3% intensity signal in **P3HT-50F** would therefore represent a TT defect ($F_{(B)}$) in approximately 1.5% of the polymer chain, hence a 98.5% regioregularity. This same reasoning leads to a regioregularity of 98% for **P3HT-33F** and 95% for **P3HT-25F**.

In the ^{19}F NMR spectrum of **P3HT-50F**, a very weak signal can be observed at -120.27 ppm. This may be produced by the small rate of TT initiation-induced homocoupling defects which, rather than occurring somewhere within the polymer chain, appear at the beginning of the chain, as was originally assumed to be the only position of the defect in KCTP-prepared polymers. One possible piece of evidence that this may be the case is that this resonance does not appear in the two other polymers. This may be due to the nature of the monomers used in that, as the rate of fluorination decreases, the fluorine atom is increasingly distant from the chain end, *i.e.* one

thiophene separates it from the terminal C-Br bond in **P3HT-50F**, two in **P3HT-33F** and three in **P3HT-25F**. Therefore, the occurrence of a TT homocoupling defect present at a chain end for **P3HT-33F** and **P3HT-25F** would be too distant from the nearest fluorine atom for the electronic environment of **P3HT-25F** to be significantly different than a TT defect within the chain.

The values of regioregularity obtained using this method offer more of an indication as to the degree of polymerization for each chain, rather than the rate of defects. Since no other clear signals indicating other defects are present, one may conclude that there is only one TT defect per polymer chain. This TT defect is then ‘diluted’ in the number of regioregular HT couplings corresponding to the degree of polymerization of the chain. Despite the imprecision of NMR analysis in giving precise ratios for high molecular weight polymers, the values of regioregularity are in relatively good agreement with those of the soluble 100% fluorinated poly(3-alkylthiophene)s synthesized by Heeney *et al.* (in which the hexyl side chain was replaced by octyl and ethylhexyl chains).¹⁴

In P3HT, DSC measurements serve as an indicator of the degree of regioregularity. A study in which defects were deliberately incorporated into the polymer chain showed a strong correlation between the regioregularity and the crystallization temperature and enthalpy.³¹ Heating and cooling traces are shown in **Figure 5**, and **Table 2** details the numerical values from these experiments, along with those of P3HT. All three samples display relatively sharp crystallization and melting peaks, indicating a high regioregularity for **P3HT-50F**, **P3HT-33F** and **P3HT-25F**. No evidence of glass transitions was found. With decreasing fluorination, the melting temperatures were 264, 254 and 250 °C, crystallization temperatures were 239, 228 and 221 °C, and crystallization enthalpies were 32, 27 and 25 J/g. The lower melting temperature and crystallization enthalpies for the polymers with a lower degree of fluorination may be due to

reduced interactions between polymer chains. Melting and crystallization temperatures for **P3HT-50F** were only slightly lower than those reported for the 100% fluorinated P3HT prepared by the same KCTP method ($T_{\text{fus,p}} = 267\text{ }^{\circ}\text{C}$ and $279\text{ }^{\circ}\text{C}$; $T_{\text{c,p}} = 245\text{ }^{\circ}\text{C}$), and unlike the 100% fluorinated poly(3-alkylthiophene)s previously reported, **P3HT-50F** possessed a single melting peak, rather than two.¹⁴ Interestingly, the crystallization enthalpy of **P3HT-50F** was equivalent to that of the all-fluorinated P3HT. All three polymers also display high thermal stability, with nearly identical degradation temperatures.

Table 2. Physical properties of **P3HT-50F**, **P3HT-33F**, **P3HT-25F**, and P3HT

Polymer	$T_{\text{fus,p}}\text{ (}^{\circ}\text{C)}^a$	$T_{\text{c,p}}\text{ (}^{\circ}\text{C)}^a$	$\Delta H(T_c)\text{ (J/g)}^a$	$T_d\text{ (}^{\circ}\text{C)}^b$
P3HT-50F	264	239	32	436
P3HT-33F	254	228	27	438
P3HT-25F	250	221	25	440
P3HT (KCTP)^c	234	198	15	464
P3HT (DHAP)^c	237	208	16	464

^a Melting temperature ($T_{\text{fus,p}}$), crystallization temperature ($T_{\text{c,p}}$) and enthalpy of crystallization ($\Delta H(T_c)$) were determined by differential scanning calorimetry (DSC) under nitrogen at a scanning speed of $10\text{ }^{\circ}\text{C/min}$. ^b Degradation temperature (T_d) was determined at 5% weight loss via thermogravimetric analysis (TGA). ^c Previously reported samples of P3HT.²⁴

Figure 5. DSC traces for the second cycle of heating and cooling for **P3HT-50F**, **P3HT-33F**, **P3HT-25F** and **P3HT** under nitrogen at a scanning speed of 10 °C/min. Endothermic transitions point downward.

3. Conformational analysis

We employed density functional theory (DFT) calculations in order to understand the intrinsic conformational preferences of **P3HT-50**, **P3HT-33** and **P3HT-25**. To reduce the computational expense and to simplify the potential energy surface, we truncated all alkyl sidechains to methyl groups with the common assumption that this modification would not substantially change their electronic properties. Our calculations were performed on model oligomers (monomers, dimers, and trimers) of the polymers studied experimentally (**Figure 6**).

Figure 6. The series of truncated fluorinated P3HT oligomers studied using DFT calculations.

We employed the B3LYP/6-311+G(d,p)-D3BJ)-IEFPCM($\epsilon=4$)/B97D/6-31G(d,p)-IEFPCM($\epsilon=4$) level of theory to find the two lowest energy conformers based on this model chemistry for **P3HT-50F-monomer**. The structures and relative energies are shown in **Figure 7**.

Figure 7. The lowest energy conformers of **P3HT-50F-monomer**. Computed using B3LYP/6-311+G(d,p)-D3BJ)-IEFPCM($\epsilon=4$)/B97D/6-31G(d,p)-IEFPCM($\epsilon=4$).

For **P3HT-50F-monomer**, the lowest energy conformer features the thiophenes pointing in opposite directions (*anti*). We refer to the dihedral angle between the two thiophenes as SCCS; the dihedral angle includes the sulfur atoms and connecting carbons between adjacent thiophenes. This conformation has a relatively distorted backbone; the SCCS dihedral angle is

28°. The structure is not planar in the gas phase because of competing S-S closed-shell repulsions and a steric clash between methyl hydrogens and the nearby sulfur lone pair orbitals (2.90 Å). The *syn* conformer of **P3HT-50F-monomer** is higher in free energy by 0.6 kcal mol⁻¹ and the backbone SCCS dihedral angle is 36°. The destabilizing S-S repulsion outweighs the CH₃-S steric clash, and we expect this class of fluorinated thiophenes to exhibit more polymorphism and disorder than thiophenes unsubstituted at the 3-position. We extended our conformational search with **P3HT-50F-dimer**; **Figure 8** shows the lowest energy conformer.

Figure 8. The lowest energy conformation of **P3HT-50F-dimer**. Computed using B3LYP/6-311+G(d,p)-D3BJ)-IEFPCM($\epsilon=4$)/B97D/6-31G(d,p)-IEFPCM($\epsilon=4$).

The lowest energy conformer features an *all-anti* relationship for the thiophene sulfurs. The central dihedral angle is virtually planar (1° rotated from planarity). De la Cruz *et al.* have suggested that S-F interactions are slightly stabilizing,³² which appears to preserve planarity about the central SCCS dihedral in **P3HT-50-dimer**. The outermost thiophenes are more distorted from planarity (14° and 22°) because of CH₃-S steric clashes identified in **Figure 8**. We then computed **P3HT-50-trimer**, but only considered the *all-syn* and *all-anti* conformers. The

all-syn conformer is higher in free energy by 1.2 kcal mol⁻¹ and is helical in the gas phase to avoid three pairs of S-S repulsions. Only the *all-anti* conformation of **P3HT-50-trimer** is considered, and is shown in **Figure 9**.

Figure 9. The all-anti conformation of **P3HT-50-trimer**, computed using B97D/6-31G(d,p)-IEFPCM($\epsilon=4$).

Wherever S-F interactions are possible, the corresponding SCCS dihedral angles are considerably more planar (2-3° vs 12-24°). Again, SCCS dihedral angles for the outermost thiophenes are larger (16° and 24°) to avoid CH₃-S steric repulsions. We report the computed HOMO and LUMO energies for these systems in **Table 3**.

Table 3. The computed frontier molecular orbitals for **1** in the *all-anti* conformations.

Truncated oligomer model	HOMO (eV)	LUMO (eV)	HOMO-LUMO gap (eV)
P3HT-50-monomer	−5.69	−1.34	4.35
P3HT-50-dimer	−5.14	−2.26	2.88
P3HT-50-trimer	−4.99	−2.51	2.48
P3HT-33-dimer	−4.91	−2.42	2.49
P3HT-25-dimer	−4.82	−2.53	2.29

Table 3 shows that the HOMO-LUMO gap is extremely large for the monomer (4.35 eV) because of the short conjugation length in this oversimplified system. The dimer and trimer approach those measured experimentally (**Table 4**, see below). Our results are consistent with many other reports of decreasing HOMO and LUMO energies with increased proportions of fluorinated backbone. The HOMO-LUMO gap is larger for **P3HT-50-dimer** than **P3HT-33-dimer** and **P3HT-25-dimer** because fluorination lowers the energy of the **P3HT-50F** HOMO more than that of the LUMO. This behavior is due to the fluorine lone pair being part of the HOMO, but not the LUMO.

For **P3HT-33** and **P3HT-25**, we computed the truncated structures **P3HT-33-dimer** and **P3HT-25-dimer** in the *all-anti* conformation and calculated the corresponding frontier molecular orbitals (**Figure 10**).

Figure 10. The structure of **P3HT-33-dimer** and **P3HT-25-dimer** with the corresponding frontier molecular orbitals. Computed using B3LYP/6-311+G(d,p)-D3BJ)-IEFPCM($\epsilon=4$)/B97D/6-31G(d,p)-IEFPCM($\epsilon=4$).

In **P3HT-33-dimer**, the SCCS dihedral angles range from 1-20° and in **P3HT-25-dimer** the dihedral angles range from 1-18°, with the central SCCS dihedral angle virtually planar (1° out of plane twist). Through-space S-F interactions reinforce the planarity and CH₃-S steric clashes increase the SCCS angles in these dimers. The extensive delocalization of the frontier molecular orbitals of **P3HT-25-dimer** relative to **P3HT-33-dimer** results in a smaller HOMO-LUMO gap (2.29 vs. 2.49 eV).

4. Polymer Optical and Electronic Properties

Solution UV-visible analyses were undertaken using a temperature gradient in order to assess the aggregation of the polymers in solution (solution and solid-state UV-visible spectra are shown in **Figure 11**, and numerical values from solution and film UV-visible spectroscopic analyses are detailed in **Table 4**). The spectra of fluorinated polymers are highly temperature-dependent, as previously reported.³³ Results indicate that **P3HT-25F** is soluble in *o*-DCB at room temperature and that **P3HT-33F** becomes fully solubilized at *ca.* 70 °C. In **P3HT-50F**, the shape of the absorbance spectrum indicates the presence of aggregates, which persist until 100 °C. Above these temperatures, all three polymers produce similar, featureless spectra with absorbance maxima at 422, 430 and 432 nm for **P3HT-50F**, **P3HT-33F** and **P3HT-25F**, respectively. The temperature-dependant evolution of the spectra was found to be reversible.

Following the observation of these aggregates at relatively high temperatures, films for solid-state absorbance spectra were spin-coated from *o*-DCB solutions at 120 °C in order to ensure the full solubility of all three polymers prior to deposition. The three polymers display almost identical absorbance spectra in the solid state, indicating similar inter- and intra-chain organization upon cooling. The two principal absorbance maxima appear at 548/596, 550/595 and 553/600 nm for **P3HT-50F**, **P3HT-33F** and **P3HT-25F**, respectively, which can be attributed to the A_{0-0} and A_{0-1} spectral transitions.³⁴ The slight variation in absorbance is not due to variation in molecular weights, as all three polymers have surpassed the effective conjugation length of poly(thiophene)s at the observed chain length.³⁵ With decreased fluorination, both spectral transitions shift towards longer wavelengths and approach the standard values of P3HT in the solid state (555/610 nm).³⁶

The ratio of the intensity of these two absorbance maxima (A_{0-0}/A_{0-1}) is comparable for the three polymers. In P3HT, a high A_{0-0}/A_{0-1} ratio is indicative of both a high regioregularity and high degree of polymerization. A substantial increase of DP would be necessary to compensate for the impact of a small reduction in regioregularity on the A_{0-0}/A_{0-1} ratio, due to the effective conjugation length in the crystallized polymer.³⁴ Consequently, the similar A_{0-0}/A_{0-1} ratios of the three polymers (0.965, 0.920 and 0.956, respectively) fits with the slight reduction in regioregularity from **P3HT-50F** to **P3HT-25F** (98%, 97% and 95%) at the same time as a relatively large increase of molecular weight values. On the other hand, as observed from NMR spectra, the only noticeable defect is the tail-to-tail homocoupling issuing from the initiation of the KCTP reaction, as discussed earlier. Unlike a head-to-head defect, a tail-to-tail defect in the polymer would likely not induce twisting of the conjugated backbone. It is possible that the presence of fluorine substituents in adjacent thiophene units may in fact *favor* localized coplanarity and rigidity. Therefore, the regioregularity may have a negligible effect on the observed A_{0-0}/A_{0-1} values.

The optical bandgap, as calculated using the solid-state UV-visible spectra, changes very little between the three polymers, indicating that both the HOMO and LUMO levels deepen in parallel with an increased rate of fluorination (numerical values of electronic measurements are given in **Table 4**). However, the observed bandgaps are slightly larger than reported values for P3HT (1.9 eV).³⁷ The bandgap is very similar to the previously reported randomly fluorinated P3HT analogues, although the bandgap increases from 1.93 in the 25% fluorinated polymer to 1.99 eV in the 100% fluorinated polymer.¹⁵ The similar bandgaps for **P3HT-50F**, **P3HT-33F** and **P3HT-25F** may be indicative of the comparable regioregularity of the three polymers.

Table 4. Optical and electronic measurements for **P3HT-50F**, **P3HT-33F** and **P3HT-25F**

Polymer	A₀₋₀ /A₀₋₁	Film ^a	Solution (RT in <i>o</i>- DCB) ^b	Solution (140 °C in <i>o</i>-DCB) ^b	E_{g opt} (eV) ^c	HOMO (eV) ^d	LUMO (eV) ^e
P3HT-50F	0.965	548, 596	548, 594	422	1.98	-5.34	-3.36
P3HT-33F	0.920	550, 595	460, 594	430	1.98	-5.26	-3.28
P3HT-25F	0.956	553, 600	462	432	1.97	-5.24	-3.27

^a Solid-state UV-visible spectra were obtained from as-spun thin films prepared via spin coating of a 2.0 mg/ml solution of the polymer in *o*-DCB at 120 °C. ^b Solution UV-visible spectra were obtained from a 0.01 mg/ml solution of the polymer heated until fully soluble in *o*-DCB and then cooled to the desired temperature for analysis. ^c Optical bandgap for each polymer was determined using the tangent of the onset of low-energy absorbance in the corresponding UV-visible spectrum. ^d The onset of oxidation was determined by cyclic voltammetry of polymer films cast on the electrode from an *o*-DCB solution; an external reference of ferrocene (Fc/Fc⁺) was used. ^e The LUMO energy was estimated by subtracting the optical bandgap (E_{g opt}) from the observed HOMO.

Figure 11. UV-visible spectra of polymers **P3HT-50F**, **P3HT-33F** and **P3HT-25F** in solution (a, b and c) and in thin films (d). Solid-state UV-visible spectra were obtained from as-spun thin films prepared via spin coating of a 2.0 mg/ml solution of the polymer in *o*-DCB at 120 °C. Solution UV-visible spectra were obtained from a 0.01 mg/ml solution of the polymer heated until fully soluble in *o*-DCB and then cooled to 30 °C, at which point the temperature was increased in 10° increments.

Cyclic voltammetry was used to compare the onset of oxidation of the three polymers with that of P3HT. Cyclic voltammograms for **P3HT-50F**, **P3HT-33F** and **P3HT-25F**, as well as for P3HT are shown in **Figure 12**, along with that of the external ferrocene reference (numerical

values are found in **Table 4**). In all three voltammograms, three oxidative doping peaks are clearly visible. Due to this similarity with the voltammograms of P3HT, it is possible that these peaks also correspond to the formation of a polaron and bipolaron. The reductive peaks are also somewhat visible in all three polymers. **P3HT-50F** shows the most narrow oxidation peaks, perhaps due to the narrow spacing of the fluorinated thiophenes which may lead to the most isoenergetic polymer chain conjugation.³⁸ The three oxidation peaks in **P3HT-25F** appear at a higher voltage than those of the two other fluorinated polymers and, in keeping with this, the onset of oxidation of **P3HT-50F**, **P3HT-33F** and **P3HT-25F** is -5.34, -5.26 and -5.24 eV, respectively, as compared to -5.18 eV for the P3HT reference polymer analyzed in the same conditions. It may be concluded that below 33%, fluorination has very little effect on the electrochemical properties of P3HT, as the oxidation onset between **P3HT-33F** and **P3HT-25F** changes very little. A parallel can be drawn here with the study of DHAP-prepared random fluorinated copolymers, the authors of which identified that the HOMO changes very little between the 50%, 75% and 100% fluorinated materials, possibly due to ‘donor’ and ‘acceptor’ effects.¹⁵ The electronic effect of the fluorine substituent on the HOMO does therefore seem to have the greatest impact somewhere between 33% and 50% substitution, and beyond this point increased fluorination only reduces solubility.

Figure 12. Cyclic voltammetry measurements for **P3HT-50F**, **P3HT-33F** and **P3HT-25F**, along with a **P3HT** sample and the external ferrocene (Fc/Fc^+) reference. Polymer films were cast onto the electrode from an *o*-DCB solution.

For comparison purposes, field effect transistors were prepared in the bottom-gate bottom-contact configuration (BGBC) to assess charge carrier mobilities in the three polymers. Due to the limited solubility of **P3HT-50F**, all polymers were deposited via spin-coating of an *o*-DCB solution. Full details of transistor preparation are available in the **Supporting Information**. Average and maximum charge carrier mobilities, on/off current ratios and threshold voltages for each polymer at these two temperatures are detailed in **Table 5**, and are accompanied by reference values for P3HT. The hole mobility of **P3HT-50F** ($0.0079 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$) and **P3HT-25F**

($0.0013 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$) were found to be optimal at 100°C and the highest average was obtained with **P3HT-33F** at 150°C ($0.0289 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$), although mobility values were comparable at these two annealing temperatures. The fact that **P3HT-33F** led to the best results was possibly due to an optimized trade-off between the increasing planarity of the polymer backbone and decreasing crystallinity when the degree of fluorination is increased, as observed in previous fluorinated polythiophenes.^{14, 15} In similarly-prepared devices, highly regioregular non-fluorinated P3HT prepared by both KCTP and DHAP displays much higher mobilities (0.08 and $0.14 \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$, respectively).²⁴ It is, however, interesting to note that on/off current ratios for all three polymers surpass not only those of non-fluorinated P3HT which was prepared in the same conditions (10^3), but also those of previously reported all-fluorinated P3HT (10^4 - 10^5).^{14, 24} The most likely explanation may be related to the deeper HOMO levels ($\sim -5.3 \text{ eV}$ as opposed to ~ -5.2 for P3HT). Indeed, the three fluorinated polymers are less susceptible to doping by ambient oxygen than P3HT, preserving their insulating properties and, by extension, limiting their electrical conductivity and minimizing their off current. No electron transport behavior was observed for any of the three polymers.

Table 5. Average and maximum mobility in field-effect transistors.

Polymer	T (°C) ^a	μ ($\times 10^{-2} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$) ^b	I _{ON/OFF} ^c	V _{TH} ^d
P3HT-50F	100	0.45 ± 0.20 (0.79)	~10 ⁵ -10 ⁶	6.9
	150	0.43 ± 0.20 (0.75)	~10 ⁶	7.1
P3HT-33F	100	2.66 ± 0.13 (2.82)	~10 ⁶	10.5
	150	2.72 ± 0.16 (2.89)	~10 ⁶ -10 ⁷	7.9
P3HT-25F	100	1.18 ± 0.07 (1.30)	~10 ⁶ -10 ⁷	7.7
	150	1.05 ± 0.07 (1.17)	~10 ⁵ -10 ⁶	1.1

^a Annealing temperature. ^b Charge carrier mobility values are written out in the form *Average* ± *standard deviation (maximum)*. ^c On/off current ratio. ^d Average threshold voltage.

Conclusion

Three derivatives of poly(3-hexylthiophene) which differ in the ratio of fluorinated thiophene repeating units were reported. **P3HT-50F**, **P3HT-33F** and **P3HT-25F** were synthesized via the Kumada catalyst transfer polymerization of monomers which were prepared in turn using iterative Migita-Stille couplings from 2-bromo-4-fluoro-3-hexylthiophene (**2Br4F3HT**). This method allowed for a regular separation of fluorine atoms along the polythiophenes backbone. Detailed ¹H and ¹⁹F NMR spectroscopic studies was undertaken, and from these it could be determined that all three polymers displayed comparable and high regioregularity. Well-defined

UV-visible absorbance spectra and sharp peaks in differential scanning calorimetry measurements both confirmed the high regioregularity of the three polymers. Computational analyses indicated that favourable fluorine-sulfur interactions contribute to the planarity of the *anti*-conformation between thiophene units of truncated models. The dihedral angle between two thiophenes is minimized when one of the thiophenes possesses a fluorine substituent in the 4-position. It was determined from this that the favourable sulfur-fluorine interaction overcomes the otherwise unfavorable sulfur-methyl steric clash. Optical bandgaps of 1.98 eV for both **P3HT-50F** and **P3HT-33F**, as opposed to 1.97 eV for **P3HT-25F**, and HOMO energy levels of -5.34, -5.26 and -5.24 eV, as determined from electrochemical measurements for **P3HT-50F**, **P3HT-33F** and **P3HT-25F**, respectively, indicated that below the 33% fluorination point, fluorination had little effect on the electrochemical properties of P3HT. **P3HT-33F** also possessed the best results in field effect transistors, reaching hole mobilities of $2.89 \times 10^{-2} \text{ cm}^2 \text{ V}^{-1} \text{ s}^{-1}$. Despite the lowering of the HOMO levels and the improved on/off current ratios, the overall OFET performances of highly regioregular P3HT are still better than those of their regioregular, evenly fluorinated counterparts.

Acknowledgements

The authors acknowledge the Natural Sciences and Engineering Research Council of Canada (NSERC) and the Canadian Institute for Advanced Research (CIFAR) for their support. J. T. B. thanks the NSERC for a Canada Graduate Scholarship, S. A. L. thanks the U.S. Department of Energy Energy Efficiency and Renewable Energy postdoctoral fellowship (Solar Energy program) for funding and J. de G. S. thanks the Brazilian Coordination for the Improvement of

Higher Education Personnel (CAPES) (Program number: Julio de Goes Soares/88888.934050/2014-00). A.A.-G. acknowledges support from the Department of Energy Basic, Energy Sciences Program in Theory and Modeling under contract DE-SC0015959. J. T. B. thanks Rodica Neagu Plesu for help with certain polymer characterization methods.

Supporting Information

Additional figures, NMR spectra, details of synthesis, computational data, MALDI-ToF data, fabrication methods for the preparation of OTFTs and device output and transfer curves.

References

1. Okamoto, T.; Nakahara, K.; Saeki, A.; Seki, S.; Oh, J. H.; Akkerman, H. B.; Bao, Z.; Matsuo, Y., Aryl-Perfluoroaryl Substituted Tetracene: Induction of Face-to-Face π - π Stacking and Enhancement of Charge Carrier Properties. *Chem. Mater.* **2011**, *23* (7), 1646-1649.
2. Stuart, A. C.; Tumbleston, J. R.; Zhou, H.; Li, W.; Liu, S.; Ade, H.; You, W., Fluorine Substituents Reduce Charge Recombination and Drive Structure and Morphology Development in Polymer Solar Cells. *J. Am. Chem. Soc.* **2013**, *135* (5), 1806-1815.
3. Chen, H.-Y.; Hou, J.; Zhang, S.; Liang, Y.; Yang, G.; Yang, Y.; Yu, L.; Wu, Y.; Li, G., Polymer solar cells with enhanced open-circuit voltage and efficiency. *Nature Photon.* **2009**, *3* (11), 649-653.

4. Liang, Y.; Feng, D.; Wu, Y.; Tsai, S.-T.; Li, G.; Ray, C.; Yu, L., Highly Efficient Solar Cell Polymers Developed via Fine-Tuning of Structural and Electronic Properties. *J. Am. Chem. Soc.* **2009**, *131* (22), 7792-7799.
5. Koster, L. J. A.; Mihailetschi, V. D.; Blom, P. W. M., Ultimate efficiency of polymer/fullerene bulk heterojunction solar cells. *Appl. Phys. Lett.* **2006**, *88* (9), 093511.
6. Yum, S.; An, T. K.; Wang, X.; Lee, W.; Uddin, M. A.; Kim, Y. J.; Nguyen, T. L.; Xu, S.; Hwang, S.; Park, C. E.; Woo, H. Y., Benzotriazole-Containing Planar Conjugated Polymers with Noncovalent Conformational Locks for Thermally Stable and Efficient Polymer Field-Effect Transistors. *Chem. Mater.* **2014**, *26* (6), 2147-2154.
7. Nguyen, T. L.; Choi, H.; Ko, S. J.; Uddin, M. A.; Walker, B.; Yum, S.; Jeong, J. E.; Yun, M. H.; Shin, T. J.; Hwang, S.; Kim, J. Y.; Woo, H. Y., Semi-crystalline photovoltaic polymers with efficiency exceeding 9% in a [similar]300 nm thick conventional single-cell device. *Energ. Environ. Sci.* **2014**, *7* (9), 3040-3051.
8. Leclerc, N.; Chávez, P.; Ibraikulov, O.; Heiser, T.; Lévêque, P., Impact of Backbone Fluorination on π -Conjugated Polymers in Organic Photovoltaic Devices: A Review. *Polymers* **2016**, *8* (1), 11.
9. El Kassmi, A.; Fache, F.; Lemaire, M., Poly(3-fluorothiophene). *J. Electroanal. Chem.* **1994**, *373* (1), 241-244.
10. Sakamoto, Y.; Komatsu, S.; Suzuki, T., Tetradecafluorosexithiophene: The First Perfluorinated Oligothiophene. *J. Am. Chem. Soc.* **2001**, *123* (19), 4643-4644.
11. Heeney, M.; Farrand, L.; Giles, M.; Thompson, M.; Tierney, S.; Shkunov, M.; Sparrowe, D.; McCullouch, I. U.S. Patent 6676857 B2, 2004.

12. Gohier, F.; Frère, P.; Roncali, J., 3-Fluoro-4-hexylthiophene as a Building Block for Tuning the Electronic Properties of Conjugated Polythiophenes. *J. Org. Chem.* **2013**, *78* (4), 1497-1503.
13. Koo, B.; Sletten, E. M.; Swager, T. M., Functionalized Poly(3-hexylthiophene)s via Lithium–Bromine Exchange. *Macromolecules* **2015**, *48* (1), 229-235.
14. Fei, Z.; Boufflet, P.; Wood, S.; Wade, J.; Moriarty, J.; Gann, E.; Ratcliff, E. L.; McNeill, C. R.; Sirringhaus, H.; Kim, J.-S.; Heeney, M., Influence of Backbone Fluorination in Regioregular Poly(3-alkyl-4-fluoro)thiophenes. *J. Am. Chem. Soc.* **2015**, *137* (21), 6866-6879.
15. Homyak, P. D.; Liu, Y.; Harris, J. D.; Liu, F.; Carter, K. R.; Russell, T. P.; Coughlin, E. B., Systematic Fluorination of P3HT: Synthesis of P(3HT-co-3H4FT)s by Direct Arylation Polymerization, Characterization, and Device Performance in OPVs. *Macromolecules* **2016**, *49* (8), 3028-3037.
16. Hoth, C. N.; Choulis, S. A.; Schilinsky, P.; Brabec, C. J., On the effect of poly(3-hexylthiophene) regioregularity on inkjet printed organic solar cells. *J. Mater. Chem.* **2009**, *19* (30), 5398-5404.
17. Gao, Y.; Zhang, X.; Tian, H.; Zhang, J.; Yan, D.; Geng, Y.; Wang, F., High Mobility Ambipolar Diketopyrrolopyrrole-Based Conjugated Polymer Synthesized Via Direct Arylation Polycondensation. *Adv. Mater.* **2015**, *27* (42), 6753-6759.
18. Bura, T.; Blaskovits, J. T.; Leclerc, M., Direct (Hetero)arylation Polymerization: Trends and Perspectives. *J. Am. Chem. Soc.* **2016**, *138* (32), 10056-10071.
19. Koch, F. P. V.; Smith, P.; Heeney, M., “Fibonacci’s Route” to Regioregular Oligo(3-hexylthiophene)s. *J. Am. Chem. Soc.* **2013**, *135* (37), 13695-13698.

20. Smith, K.; Barratt, M. L., Highly Selective 5-Substitution of 3-Methylthiophene via Directed Lithiation. *J. Org. Chem.* **2007**, *72* (3), 1031-1034.
21. Loewe, R. S.; Khersonsky, S. M.; McCullough, R. D., A Simple Method to Prepare Head-to-Tail Coupled, Regioregular Poly(3-alkylthiophenes) Using Grignard Metathesis. *Adv. Mater.* **1999**, *11* (3), 250-253.
22. Loewe, R. S.; Ewbank, P. C.; Liu, J.; Zhai, L.; McCullough, R. D., Regioregular, Head-to-Tail Coupled Poly(3-alkylthiophenes) Made Easy by the GRIM Method: Investigation of the Reaction and the Origin of Regioselectivity. *Macromolecules* **2001**, *34* (13), 4324-4333.
23. Miyakoshi, R.; Yokoyama, A.; Yokozawa, T., Catalyst-Transfer Polycondensation. Mechanism of Ni-Catalyzed Chain-Growth Polymerization Leading to Well-Defined Poly(3-hexylthiophene). *J. Am. Chem. Soc.* **2005**, *127* (49), 17542-17547.
24. Pouliot, J.-R.; Wakioka, M.; Ozawa, F.; Li, Y.; Leclerc, M., Structural Analysis of Poly(3-hexylthiophene) Prepared via Direct Heteroarylation Polymerization. *Macromol. Chem. Phys.* **2016**, *217* (13), 1493-1500.
25. Xiao, S. S.; Qiu, C.; Qiu, C. X. U.S. Patent 6894145 B2, 2005.
26. Winter, J. D.; Deshayes, G.; Boon, F.; Coulembier, O.; Dubois, P.; Gerbaux, P., MALDI-ToF analysis of polythiophene: use of trans-2-[3-(4-t-butyl-phenyl)-2-methyl-2-propenylidene]malononitrile—DCTB—as matrix. *J. Mass Spectrom.* **2011**, *46* (3), 237-246.
27. Liu, J.; Loewe, R. S.; McCullough, R. D., Employing MALDI-MS on Poly(alkylthiophenes): Analysis of Molecular Weights, Molecular Weight Distributions, End-Group Structures, and End-Group Modifications. *Macromolecules* **1999**, *32* (18), 5777-5785.
28. Komber, H.; Senkovskyy, V.; Tkachov, R.; Johnson, K.; Kiriy, A.; Huck, W. T. S.; Sommer, M., Ring Walking versus Trapping of Nickel(0) during Kumada Catalyst Transfer

Polycondensation Using Externally Initiated Electron-Accepting Thiophene–Benzothiadiazole–Thiophene Precursors. *Macromolecules* **2011**, *44* (23), 9164-9172.

29. Holdcroft, S., Determination of molecular weights and Mark–Houwink constants for soluble electronically conducting polymers. *J. Polym. Sci., Part B: Polym. Phys.* **1991**, *29* (13), 1585-1588.

30. Kiriya, A.; Senkovskyy, V.; Sommer, M., Kumada Catalyst-Transfer Polycondensation: Mechanism, Opportunities, and Challenges. *Macromol. Rapid Commun.* **2011**, *32* (19), 1503-1517.

31. Kim, J.-S.; Kim, J.-H.; Lee, W.; Yu, H.; Kim, H. J.; Song, I.; Shin, M.; Oh, J. H.; Jeong, U.; Kim, T.-S.; Kim, B. J., Tuning Mechanical and Optoelectrical Properties of Poly(3-hexylthiophene) through Systematic Regioregularity Control. *Macromolecules* **2015**, *48* (13), 4339-4346.

32. Jackson, N. E.; Savoie, B. M.; Kohlstedt, K. L.; Olvera de la Cruz, M.; Schatz, G. C.; Chen, L. X.; Ratner, M. A., Controlling Conformations of Conjugated Polymers and Small Molecules: The Role of Nonbonding Interactions. *J. Am. Chem. Soc.* **2013**, *135* (28), 10475-10483.

33. Li, Z.; Lin, H.; Jiang, K.; Carpenter, J.; Li, Y.; Liu, Y.; Hu, H.; Zhao, J.; Ma, W.; Ade, H.; Yan, H., Dramatic performance enhancement for large bandgap thick-film polymer solar cells introduced by a difluorinated donor unit. *Nano Energy* **2015**, *15*, 607-615.

34. Kohn, P.; Huettner, S.; Komber, H.; Senkovskyy, V.; Tkachov, R.; Kiriya, A.; Friend, R. H.; Steiner, U.; Huck, W. T. S.; Sommer, J.-U.; Sommer, M., On the Role of Single Regiodefects and Polydispersity in Regioregular Poly(3-hexylthiophene): Defect Distribution, Synthesis of

Defect-Free Chains, and a Simple Model for the Determination of Crystallinity. *J. Am. Chem. Soc.* **2012**, *134* (10), 4790-4805.

35. Zhang, L.; Colella, N. S.; Liu, F.; Trahan, S.; Baral, J. K.; Winter, H. H.; Mannsfeld, S. C. B.; Briseno, A. L., Synthesis, Electronic Structure, Molecular Packing/Morphology Evolution, and Carrier Mobilities of Pure Oligo-/Poly(alkylthiophenes). *J. Am. Chem. Soc.* **2013**, *135* (2), 844-854.

36. Perepichka, I. F.; Perepichka, D. F., *Handbook of Thiophene-based Materials: Applications in Organic Electronics and Photonics*. John Wiley and Sons, Ltd. : 2009; Vol. 1, p 417.

37. McCullough, R. D., The Chemistry of Conducting Polythiophenes. *Adv. Mater.* **1998**, *10* (2), 93-116.

38. Trznadel, M.; Pron, A.; Zagorska, M.; Chrzaszcz, R.; Pielichowski, J., Effect of Molecular Weight on Spectroscopic and Spectroelectrochemical Properties of Regioregular Poly(3-hexylthiophene). *Macromolecules* **1998**, *31* (15), 5051-5058.